

DURANT

PERFORMANCE COATINGS

112 RAILROAD ST., REVERE, MA 02151

(800) 420-0021; (781) 289-1400; (781) 289-1405 (FAX)

www.durantcorp.com

DUR-A-PLEX Ultra 4800

INTERIOR ALKYD LIGHT INDUSTRIAL GLOSS ENAMEL

[Conforms to Master Painter Institute #48 Specifications]

Product Number: DUR-A-PLEX Ultra 4800

Description: Interior Alkyd Gloss Light Industrial Enamel for interior use with excellent hiding properties combined with a uniform high gloss finish.

Average Dry Time at 75°F(24°C):

4 hrs (dry to touch); 8 hrs for 2nd coat application, 7 days full cure

Suggested Use: Use on interior primed or previously painted surfaces. Ideal for use on doors, window sash or trim, plywood or hardboard construction or primed or previously painted metal surfaces.

Reducer:

Not Recommended

Suggested Clean Up:

Mineral Spirits

Application:

Brush, Roller or Spray

NOTE: Do not apply if material, substrate or ambient temperature is below 45°F(7°C) or above 95°F(35°C). Best if relative humidity is below 80%.

Colors: White & Custom Colors

Finish: High Gloss

Vehicle Type: Alkyd Resin

Surface Preparation:

Remove all loose dirt, rust, oil, grease, excess moisture and other foreign matter.

Solvent Type: Aliphatic Hydrocarbon

VOC: 340 g/l (2.8 #/gal)

Shelf Life:

12 months

Flash Point: 103°F(39°C)

Mixing:

Stir until thoroughly homogenized

Solids by Volume: 50.6 %

Weight per Gallon : 10.06 lbs.

Caution:

Contents are COMBUSTIBLE. Keep away from heat and open flame. VAPOR HARMFUL. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If

Recommended Dry Film: 2.5-3.0 dry mil

Coverage: Theoretical coverage at one mil dry = 812 square feet (estimate does not include normal material losses during mixing and application process).

Viscosity at 75°F(24°C): 85-95 KU

adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage.

FIRST AID: In case of eye contact, flush thoroughly with large amounts of water for 15 minutes and get medical attention. For skin contact, wash thoroughly with soap and water. In case of respiratory difficulty, provide fresh air and call physician. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately.

Delayed Effects from Long term Overexposure. Contains solvents which can cause permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents can be harmful or fatal. Reports have associated repeated or prolonged overexposure to solvents with permanent brain and nervous system damage.

**DO NOT TAKE INTERNALLY.
KEEP OUT OF THE REACH OF
CHILDREN.**

Packaging: 1 Gallon Cans (4 per case)
5 Gallon Pails

The Information and recommendations contained in this Product Data Sheet are based upon tests conducted by or on behalf of Durant Performance Coatings, Inc. and are accurate to the best of our knowledge. The information and recommendations contained herein are subject to change.

Workmanship, weather, equipment, quality of other materials used or other variables may affect results. Contact Durant Performance Coatings, Inc. with any questions or comments.